

This page is mainly introduced the 1.4418 chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 1.4418, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels 1.4418

| 1.4418 Standard Number: | | | | |
|-------------------------|-----------------|--|--|--|
| ITEM | Standard Number | Descriptions | | |
| 1 | BS EN 10028-7 | Flat products made of steels for pressure purposes - Part 7: Stainless steels | | |
| 2 | BS EN 10088-1 | Stainless steels - Part 1: List of stainless steels | | |
| 3 | BS EN 10088-2 | Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes | | |
| 4 | BS EN 10088-3 | Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes | | |
| 5 | BS EN 10088-4 | Stainless steels - Part 4: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for construction purposes | | |
| 6 | BS EN 10088-5 | Stainless steels - Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes | | |
| 7 | BS EN 10250-4 | Open die steel forgings for general engineering purposes - Part 4: Stainless steels | | |
| 8 | BS EN 10272 | Stainless steel bars for pressure purposes | | |

| 1.4418 Chemical composition(mass fraction)(wt.%) | | | | |
|--|---------|---------|--|--|
| Chemical | Min.(%) | Max.(%) | | |
| С | | 0.06 | | |
| Si | | 0.70 | | |
| Mn | | 1.50 | | |
| Р | | 0.04 | | |
| S | | 0.015 | | |
| Cr | 15.00 | 17.00 | | |
| Ni | 4.00 | 6.00 | | |
| Мо | 0.80 | 1.50 | | |
| N | 0.020 | | | |

| 1.4418 Physical Properties | | | |
|----------------------------|---------|-------------|--|
| Tensile strength | 115-234 | σb/MPa | |
| Yield Strength | 23 | σ 0.2 ≥/MPa | |

Email: sales@tool-die-steels.com http://www.tool-die-steels.com/ Page 1 / 2

1.4418 Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

| Elongation | 65 | δ5≥ (%) |
|------------|---------|---------|
| Ψ | - | |
| Akv | - | Akv≥/J |
| HBS | 123-321 | - |
| HRC | 30 | - |

| 1.4418 Mechanical Properties | | | | |
|------------------------------|---------|-------------|--|--|
| Tensile strength | 231-231 | σb/MPa | | |
| Yield Strength | 154 | σ 0.2 ≥/MPa | | |
| Elongation | 56 | δ5≥(%) | | |
| Ψ | - | ψ≥(%) | | |
| Akv | - | Akv≥/J | | |
| HBS | 235-268 | - | | |
| HRC | 30 | - | | |

| 1.4418 Heat Treatment Regime | | | | |
|------------------------------|-----------|-----------|-------------|-------|
| Annealing | Quenching | Tempering | Normalizing | Q & T |
| V | √ | √ | V | √ |

| 1.4418 Range of products | | | | |
|--------------------------|---|-------------------------------|---|--|
| Product type | Products | Dimension | Processes | Deliver Status |
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting |
| Steel Bar | Round Bar, Flat Bar, Square Bar | Φ8-1200mm*L | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting, |
| Coil / Strip | Steel Coil /Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot- Rolled | Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting |
| Pipes / Tubes | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded | Annealed, Solution and Aging, Q+T, ACID- WASHED |

We can produce Stainless Steels the specifications follows: