

This page is mainly introduced the X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Data Table for Grades Stainless Steels X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2

X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 Standard Number:

ITEM	Standard Number	Descriptions
1	EN 10088-1	Stainless steels - Part 1: List of stainless steels
2	EN 10088-3	Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes
3	EN 10088-5	Stainless steels - Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes
4	EN 10263-5	Steel rod, bars and steel wire for cold heading and cold extrusion - Part 5: Technical delivery conditions for stainless steels
5	EN 10269	Steels and nickel alloys for fasteners with specified elevated and/or low temperature properties

X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 Chemical composition(mass fraction)(wt.%)

Chemical	Min.(%)	Max.(%)
C		0.04
Si		1.00
Mn		2.00
P		0.045
S		0.015
Cr	17.00	19.00
Ni	8.50	10.50
Mo		
N		0.11
Cu	3.00	4.00

X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 Physical

Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv $\geq$ /J
HBS	123-321	-
HRC	30	-

X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv $\geq$ /J
HBS	235-268	-
HRC	30	-

X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

X3CrNiCu18-9-4, 1.4567, 1.4560, X3CrNiCu19-9-2 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

□ □ □□ □□□ □□□□□□□□□□□□□□□□