

This page is mainly introduced the 1.2319 chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 1.2319, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Data Table for Grades Tool Die Steels 1.2319

### 1.2319 Standard Number:

ITEM	Standard Number	Descriptions
------	-----------------	--------------

### 1.2319 Chemical composition (mass fraction) (wt.%)

Chemical	Min.(%)	Max.(%)
C	0.60	0.70
Si	0.30	0.50
Mn	0.40	0.60
P		0.025
S		0.025
Cr	13.50	14.50
Mo	0.50	0.70
V	0.05	0.15

### 1.2319 Physical Properties

Tensile strength	115-234	$\sigma_b$ /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_5 \geq$ (%)
$\psi$	-	$\psi \geq$ (%)
Akv	-	Akv $\geq$ /J
HBS	123-321	-
HRC	30	-

### 1.2319 Mechanical Properties

Tensile strength	231-231	$\sigma_b$ /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta_5 \geq$ (%)
$\psi$	-	$\psi \geq$ (%)

Akv	-	Akv $\geq$ J
HBS	235-268	-
HRC	30	-

### 1.2319 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

### 1.2319 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

**We can produce Tool Die Steels the specifications follows:**